

Spontaneous Fluxoid Formation in Superconducting Loops*

R. Monaco

*Istituto di Cibernetica del CNR, 80078, Pozzuoli,
Italy and Unità INFN Dipartimento di Fisica,
Università di Salerno, 84081 Baronissi, Italy[†]*

J. Mygind

DTU Physics, B309, Technical University of Denmark, DK-2800 Lyngby, Denmark[‡]

R. J. Rivers

Blackett Laboratory, Imperial College London, London SW7 2AZ, U.K. [§]

V. P. Koshelets

*Kotel'nikov Institute of Radio Engineering and Electronics Russian Academy of Science,
Mokhovaya 11, Bldg 7, 125009, Moscow, Russia.[¶]*

(Dated: July 15, 2009)

Abstract

We report on the first experimental verification of the Zurek-Kibble scenario in an isolated superconducting ring over a wide parameter range. The probability of creating a single flux quantum spontaneously during the fast normal-superconducting phase transition of a wide Nb loop clearly follows an allometric dependence on the quenching time τ_Q , as one would expect if the transition took place as fast as causality permits. However, the observed Zurek-Kibble scaling exponent $\sigma = 0.62 \pm 0.15$ is two times larger than anticipated for large loops. Assuming Gaussian winding number densities we show that this doubling is well-founded for small annuli.

PACS numbers: 11.27.+d, 05.70.Fh, 11.10.Wx, 67.40.Vs

The Zurek-Kibble (ZK) scenario [1, 2, 3] proposes that continuous phase transitions take effect as fast as possible i.e. the domain structure after the quenching of the system initially reflects the causal horizons. This proposal can be tested directly for transitions whose domain boundaries carry visible topological charge. In this letter we shall show that, with qualifications, this scenario is strongly corroborated by the behaviour of superconducting loops, for which the topological defect is a fluxoid i.e. a supercurrent vortex carrying one magnetic flux quantum $\Phi_0 = h/(2e) \simeq 2.08 \times 10^{-15} \text{ Wb}$.

The basic scenario is very simple. Consider a planar low- T_c superconductor in which a hole has been made of circumference C . In the Meissner state the order parameter for the superconductor is a complex field ψ with phase ϕ , $\psi = \rho e^{i\phi}$, where $|\rho|^2$ measures the density of Cooper pairs. On quenching the system from the normal to superconducting phase, causality prevents the system from adopting a uniform phase. If, on completion of the quench, we follow the periodic phase $\phi(x) \pmod{2\pi}$ along the boundary of the hole (co-ordinate x), we can define a winding number density: $n(x) = d\phi(x)/dx/(2\pi)$. The total normalized magnetic flux through the hole is, in units of Φ_0 , the winding number:

$$n = \int_0^C n(x) dx = \frac{\Delta\phi}{2\pi}, \quad (1)$$

where $\Delta\phi$ is the change in ϕ . In the absence of an external magnetic field, on average $\langle n \rangle = 0$, but it will have non-zero variance $(\Delta n)^2 = \langle n^2 \rangle$, which is what can be measured in terms of the probabilities $f_{\pm m}$ to trap $\pm m$ flux quanta: $\langle n^2 \rangle = \sum_{m=-\infty}^{\infty} m^2 f_m$. According to Ref.[2], on completion of a thermal quench having a given inverse quench rate $\tau_Q = -T_c/(dT/dt)_{T=T_c}$, the phase ϕ is correlated over distances $2\pi\bar{\xi}$, where $\bar{\xi}$ was predicted to depend allometrically[2] on the quench time τ_Q :

$$\bar{\xi} \approx \xi_0 \left(\frac{\tau_Q}{\tau_0} \right)^\sigma. \quad (2)$$

$\bar{\xi}$, also called the ZK causal length, is defined in terms of the cold correlation length ξ_0 and the Ginzburg-Landau relaxation time τ_0 of the long wavelength modes. The ZK scaling exponent σ is determined by the *static* critical exponents of the system and, in the mean-field approximation, $\sigma = 1/4$ [1]. If we make the further assumption that there is a random walk in phase on a scale $2\pi\bar{\xi}$ then, for a hole of radius r , circumference $C \gg 2\pi\bar{\xi}$,

$$\langle n^2 \rangle \approx \frac{C}{2\pi\xi} = \frac{r}{\xi_0} \left(\frac{\tau_Q}{\tau_0} \right)^{-\sigma}. \quad (3)$$

For small rings with $C < 2\pi\xi$ the likelihood of seeing two or more units of flux is small and $\langle n^2 \rangle \approx f_{+1} + f_{-1} = f_1$, the probability of single fluxoid trapping. It is plausible to extrapolate Eq.(3) to:

$$f_1 \approx \langle n^2 \rangle \approx \frac{r}{\xi_0} \left(\frac{\tau_Q}{\tau_0} \right)^{-\sigma}, \quad (4)$$

showing allometric behaviour of f_1 with the *same* exponent. We note that the ZK argument makes no assumptions about the rest of the superconductor, equally valid for the phase change along the inner circumference of an annulus as it is for the phase change around a single hole in a superconducting sheet. In 2003 the first experiment with superconducting loops [4] was performed to test Eq.(3). The experiment consisted of taking an isolated array of thin-film wide rings and making it undergo a forced phase transition by heating it above its superconducting critical temperature and letting it to cool passively back towards the *LHe* temperature. Once the thermal cycle is over, the rings are inspected by a scanning SQUID and the number and polarity of any trapped fluxoids determined. These rings, of amorphous Mo_3Si thin films, had thickness almost one order of magnitude smaller than the low temperature London penetration depth. Although this provides favorable conditions for thermally activated phenomena it drastically increases the likelihood that nucleated vortices escape through the ring walls during the fast quench. In fact, the experimental outcome was totally at variance with the allometric scaling above. However, the prediction Eq.(3) presupposes that we can ignore the contribution to the flux from the freezing in of thermal fluctuations of the magnetic field [5] and the results of [4] could be explained in terms of the freezing of thermally activated fluxoids in a similar spirit to Ref.[5].

In this paper we shall present results from a new experiment with high-quality Nb film rings with $r = 30\mu\text{m}$, two times thicker than their low temperature London penetration length $\lambda_{L,Nb}$; the film thickness and composition were chosen to reduce the thermal activation of fluxoids and, at the same time, 'the washing out' of fluxoids generated by the conventional causality mechanism. In our case the contribution Δf_1 to the probability of finding a unit of flux from thermal magnetic field fluctuations is approximately[5]:

$$\Delta f_1 \lesssim (k_B T_c) r \mu_0 / \Phi_0^2 \approx 6 \times 10^{-4}, \quad (5)$$

and can be safely ignored. We therefore look for scaling behaviour in τ_Q .

Here a different way of counting both the number and the polarity of generated defects has been adopted. It is based on the detection of the persistent currents $\mathbf{J}_s$ circulating around a hole in a superconducting film, when one or more fluxoids are trapped inside the hole. The circulating currents screening the bulk of the superconductor from the trapped flux induce a magnetic field $\mathbf{H}$ in the volume around the ring, such that $\mathbf{J}_s = \nabla \mathbf{x} \mathbf{H}$. By placing a Josephson tunnel junction (JTJ) along the perimeter of the hole in the area where this field passes, any trapped fluxoid will result in a modulation of the JTJ critical current, similar to the effect of an external field applied perpendicular to the ring. Indeed, this method is strongly inspired by the results found investigating the effects of a transverse field on Josephson junctions of various geometries[6]. The geometry of our experiment is sketched in Fig.1; the black wide ring is a 200 nm thick Nb film, which also acts as the common base electrode for two JTJs whose top electrodes are depicted in grey. The JTJs have the shape of gapped annuli and the bias current is supplied in their middle point: to our knowledge, this geometrical configuration has never been realized before and is characterized by a peculiar magnetic diffraction pattern: for small magnetic fields the critical current increases both for positive and negative field values. The original purpose of having two counter electrodes on the base ring was that any screening current circulating on the outer ring circumference will preferentially affect the outermost JTJ, and vice versa for the screening current on the inside of the ring. Since the persistent currents due to trapped flux mainly flow in the inner ring circumference [7], in this experiment we only used the innermost JTJ. The layout shown in Fig.1, with a few key differences, bears remarkable topological similarity to the one used in a series of experiments by us to demonstrate the ZK scaling behaviour of Eq.(3) in annular JTJs [8, 9, 10, 11, 12]. The most obvious difference in the design is the inclusion of the two junction counter electrodes on top of the ring-shaped base electrode. The second change is the removal of a small section of the full annular junction to leave a gapped annular junction with the purpose of avoiding fluxons created inside the JTJ at the Josephson phase transition. Should any be produced, they will simply migrate through the junction extremities driven by the applied bias current needed to overcome eventual pinning potentials. This leaves the experiment only sensitive to the fluxoids produced in the ring at




FIG. 1: Sketch of a superconducting loop (black) used as a base electrode for two gapped Nb/AlOx/Nb annular Josephson tunnel junctions (whose top electrodes are in gray). The ring inner and outer radii are $r = 30$ and $R = 50\mu\text{m}$, respectively, while the top electrodes width is $5\mu\text{m}$.

the phase transition.

As with our previous experiments, the present one relies on a fast heating system, obtained by integrating a Mo resistive meander line on the $4.2\text{mm} \times 3\text{mm} \times 0.35\text{mm}$ Si chip containing the ring with the Nb/AlOx/Nb JTJs. The quench time τ_Q could be continuously varied over more than four orders of magnitude (from 20 s down to 1 ms) by varying the width and the amplitude of the voltage pulse across the integrated resistive element. In order to determine the quench time with high accuracy, the ring temperature was monitored exploiting the well known temperature dependence of the gap voltage of high-quality Nb/AlOx/Nb JTJs already described in Ref.[10]. After each ring thermal quench the critical current of the innermost JTJ is automatically stored and an algorithm has been developed for the counting of the trapped fluxoids. Finally, all the measurements have been carried out in a magnetic and electromagnetically shielded environment. During the thermal quenches all electrical connections to the heater as well as to the JTJs were disconnected. While more details on the measurement setup and on the fabrication process can be found in Ref.[13] and Ref.[14], respectively, an extensive description of the chip layout, the experimental setup and the system calibration will be given elsewhere[15].

The experimental results shown in Fig. 2 were obtained using a ring with inner and outer radii, $r = 30\mu\text{m}$ and $R = 50\mu\text{m}$, respectively. Similar samples have shown the same behaviour. We note that wider rings prevent fluxoids from tunneling out of the ring,

although their smaller normal self-inductance L_n makes fluxoid formation energetically more unlikely. In our case, the field energy $E_0 = \Phi_0^2/2L_n$ associated with a single flux quantum Φ_0 is several orders of magnitude larger than the thermal energy $k_B T_c/2$ at T_c [16].

Magnetostatic numerical simulations implemented in the COMSOL Multiphysics 3D Electromagnetics module showed that, when a single flux quantum is trapped in such rings, the radial magnetic field induced by the circulating currents at the ring inner border is as large as 1A/m, a value easily detectable by the JTJ. For our rings, the number of trapped fluxoids was small, usually no more than one; indeed we measured the probability of trapping a single up-fluxoid (field up) f_{+1} and a single down-fluxoid f_{-1} .

Fig. 2 shows on a log-log plot the measured frequency $f_1 = f_{+1} + f_{-1} = (n_{+1} + n_{-1})/N = n_1/N$ of single fluxoid trapping, obtained by quenching the sample N times for each value of a given quenching time τ_Q , n_1 being the number of times that one defect or one anti-defect was spontaneously produced. N ranged between 250 and 300 and n_1 was never smaller than 10, except for the rightmost point for which $n_1 = 5$. The vertical error bars gives the statistical error $f_1/\sqrt{n_1}$. The relative error bars in τ_Q amounting to $\pm 10\%$ are as large as the dot's width. As expected we had $n_{+1} \approx n_{-1}$, but slightly larger than n_{-1} indicating the presence of a small residual stray field in our apparatus (see inset of Fig.2).

To test Eq.(2), we have fitted the data with an allometric function $f_1 = a \tau_Q^{-b}$, with a and b as free fitting parameters. An instrumentally weighted least-mean-square fit of f_1 vs. τ_Q , represented by the continuous line in Fig. 2, yields $a = 0.18 \pm 0.02$ (taking τ_Q in ms) and $b = 0.62 \pm 0.15$. The large fit correlation coefficient $R^2 = 0.987$ indicates that the allometric behaviour is reliably confirmed, however the scaling exponent b is about two times larger than expected for large loops.

A *doubling* of the large-loop ZK exponent for small loops has a possible explanation in the framework of the Gaussian correlation model introduced in Ref.[12] in which it was assumed that the winding number $n(x)$ is a *Gaussian* variable until the transition is complete, whereby all correlation functions are determined by the two-point correlation function $g(x_1 - x_2, C) = \langle n(x_1) n(x_2) \rangle$. As a result [17]:

$$\langle n^2 \rangle = \int_0^C \int_0^C \langle n(x_1) n(x_2) \rangle dx_1 dx_2 = 2C \int_0^C g(x, C) dx. \quad (6)$$

For $C \ll 2\pi\bar{\xi}$, we can assume a correlation function of the form $g(x, C) = \bar{g}(x/2\pi\bar{\xi}, C/2\pi\bar{\xi})/(2\pi\bar{\xi})^2$, so that:




FIG. 2: Log-log plot of the measured frequency f_1 of trapping single fluxoid versus the quenching time τ_Q for a Nb ring having inner radius $r = 30\mu\text{m}$, outer radius $R = 50\mu\text{m}$ and thickness $d = 200\text{nm} \simeq 2\lambda_{L,Nb}$. Each point corresponds to hundreds of thermal cycles. The vertical error bars gives the statistical error, while the relative error bars in τ_Q amounting to $\pm 10\%$ are as large as the dots' width. The solid line is the best fit to an allometric relationship $f_1 = a\tau_Q^{-b}$ which yields $a = 0.18 \pm 0.02$ (taking τ_Q in ms) and $b = 0.62 \pm 0.15$. For comparison purposes, the dashed line is the prediction of Eq.(9)) with χ (see text) set to 0.7 to fit in ordinate scale.

$$f_1 \approx 2 \frac{C}{2\pi\xi} \int_0^{C/2\pi\bar{\xi}} \bar{g}(\bar{x}, C/2\pi\bar{\xi}) d\bar{x} \approx 2 \left(\frac{C}{2\pi\bar{\xi}} \right)^2 \bar{g}(0, C/2\pi\bar{\xi}). \quad (7)$$

provided $\bar{g}(\bar{x}, C/2\pi\bar{\xi})$ is analytic at $\bar{x} = 0$. This suggests that Eq.(4) should be replaced by the scaling behaviour:

$$f_1 \approx \kappa \left(\frac{C}{2\pi\bar{\xi}} \right)^2 = \kappa \left(\frac{r}{\xi_0} \right)^2 \left(\frac{\tau_Q}{\tau_0} \right)^{-2\sigma}, \quad (8)$$

with a proportionality constant κ of the order of unity. To buttress this suggestion, it is not difficult to show that, in the Gaussian approximation, the value of $\langle n^2 \rangle$ along a small ring in a 2D superconductor is proportional to the area enclosed by the ring [15].

This doubling of the scaling exponent in Eq.(8) has the price of coming with a lower probability, but leaves us with some freedom with the ZK prefactor. Indeed, the value of the prefactor a obtained from the allometric best fit of the experimental data in Fig.2 is about $\kappa = 4\text{-}5$ times larger than the predicted value $(r/\xi_0)^2 \sqrt{\tau_0} = 0.04$ obtained using the values $r = 30\mu\text{m}$, $\xi_0 \approx 30\text{nm}$ and $\tau_0 = \pi\hbar/16k_B T_c \approx 0.16\text{ps}$ and taking τ_Q in ms. As a bound we

only expect agreement in the overall normalization of the prefactor a to somewhat better than an order of magnitude, largely confirmed by experiment. We point out that the dependence of the prefactor a on the ring width remains to be investigated both theoretically and experimentally. [We note that, if Eq.(3) were true, then $\langle n^2 \rangle$ would be ≈ 0.6 , i.e., 20 times larger than the experimental value for $\tau_Q = O(10ms)$, say.]

In the opposite case of *large* circumferences, $C \gg 2\pi\bar{\xi}$, $g(x, C)$ is controlled by the correlation length $\bar{\xi}$ of the winding number at the time of unfreezing and does not depend on C , i.e., the effect of periodicity for large rings is small. With $g(x) = \bar{g}(x/2\pi\bar{\xi})/(2\pi\bar{\xi})^2$ on dimensional grounds, we justify the random walk assumption of Eq.(3),

$$\langle n^2 \rangle = \frac{C}{\pi\bar{\xi}} \int_0^{C/2\pi\bar{\xi}} \bar{g}(z) dz \approx \frac{C}{\pi\bar{\xi}} \int_0^\infty \bar{g}(z) dz = \chi \frac{C}{2\pi\bar{\xi}}, \quad (9)$$

with $\chi = O(1)$. The dashed line in Fig.2 is the prediction in Eq.(9) with χ set to 0.7 to fit to the ordinate scale.

In summary, our experiment shows reliable scaling behaviour of the form Eq.(3) for the creation of a single fluxoid, with scaling exponent 0.62 ± 0.15 . This is obviously at variance with the extrapolation (4) of the Zurek prediction Eq.(3) to small rings, for which we expect $\sigma = 0.25$. We have suggested that it be given by Eq.(8) with twice the exponent, as a consequence of the Gaussianity of the Cooper pair field phase (before truncation by back-reaction), an assumption supported in a slightly different context by the behaviour of JTJs in an external field [12]. As Gaussianity permits the instabilities from which defects form to grow as fast as possible, in general it gives the same scaling exponents as the ZK scenario for large systems. With this qualification we see our result as providing strong support for Zurek-Kibble scaling over a wide range of quenching time τ_Q . We stress that this experiment is the *only* one to date to have confirmed the Zurek-Kibble causality scenario for single isolated superconducting rings (as distinct from Josephson junctions). Further experiments to investigate the transition to the random walk regime and the effect of the ring width are planned. For example, a test of Gaussianity is that $f_1 \lesssim 0.5$ for all values of C [12]. Given that the original ZK scenario was posed to demonstrate the similarity in the role of causality at transitions in the early Universe and in condensed matter systems we have seen that the finiteness of the latter systems requires careful disentangling from the underlying principles before we can draw any quantitative conclusions.

In the same vein we conclude with a speculation concerning the small-annulus JTJ exper-

iments [9, 10, 11, 12] that, hitherto, have been the only superconductor experiments to show scaling behaviour. In that case also, the observed exponent was twice that anticipated from long annuli [8]. However, in the case of JTJs there is an ambiguity in their fabrication that is sufficient to double the exponent, according as the 'proximity effect' enables otherwise subcritical behaviour of the Josephson current density to dominate near the transition [10]. We had assumed that this was the reason for the discrepancy. We shall now reexamine these earlier experiments with the above analysis in mind.

The authors thank P. Dmitriev for the sample fabrication and testing, A. Gordeeva for useful discussions and M. Aaroe for the help at the initial stage of the experiment.

* Submitted to Phys. Rev. Letts.

† Electronic address: roberto@sa.infn.it

‡ Electronic address: myg@fysik.dtu.dk

§ Electronic address: r.rivers@imperial.ac.uk

¶ Electronic address: valery@hitech.cplire.ru

- [1] W.H. Zurek, *Nature* **317**, 505 (1985), *Acta Physica Polonica* **B24**, 1301 (1993).
- [2] W.H. Zurek, *Physics Reports* **276**, Number 4, Nov. 1996.
- [3] T.W.B. Kibble, in *Common Trends in Particle and Condensed Matter Physics*, *Physics Reports* **67**, 183 (1980).
- [4] J.R. Kirtley, C. C. Tsuei, and F. Tafuri, *Phys. Rev. Lett.* **90**, 257001 (2003).
- [5] M. Hindmarsh and A.Rajantie, *Phys. Rev. Lett.* **85**, 4660 (2000); A. Rajantie, *J. Low Temp. Phys.* **124**, 5 (2001).
- [6] R. Monaco, M. Aaroe, J. Mygind and V.P. Koshelets, *J. Appl. Phys.* **104**, 023906 (2008).
- [7] A.A. Babaei Brojeny and J.R. Clem, *Phys. Rev. B* **67**, 174514 (2003); E.H. Brandt and J.R. Clem, *Phys. Rev. B* **69**, 184509 (2004);
- [8] E. Kavoussanaki, R. Monaco and R.J. Rivers, *Phys. Rev. Lett.* **85**, 3452 (2000).
- [9] R. Monaco, J. Mygind, and R. J. Rivers, *Phys. Rev. Lett.* **89**, 080603 (2002).
- [10] R. Monaco, J. Mygind, and R. J. Rivers, *Phys. Rev. B* **67**, 104506 (2003).
- [11] R. Monaco, J. Mygind, M. Aaroe, R.J. Rivers and V.P. Koshelets, *Phys. Rev. Lett.* **96**, 180604 (2006).

- [12] R. Monaco, J. Mygind, M. Aaroe, R.J. Rivers and V.P. Koshelets, *Phys. Rev. B* **77**, 054509 (2008); R. Rivers, R. Monaco, J. Mygind, M. Aaroe, and V.P. Koshelets, *Phil. Trans. of the Royal Society* **A366**, 2781-2880 (2008).
- [13] R. Monaco, M. Aaroe, J. Mygind and V.P. Koshelets, *Phys. Rev. B* **79**, 144521 (2009).
- [14] L.V. Filippenko, S.V. Shitov, P.N. Dmitriev, A.B. Ermakov, V.P. Koshelets, and J.R. Gao, *IEEE Trans. on Appl. Supercond.* , 816-819 (2001).
- [15] R. Monaco, J. Mygind, R.J. Rivers, and V.P. Koshelets, in preparation.
- [16] $L_n = \mu_0 r [\ln(8r/\Delta r) - 1/2] \simeq 75 \text{ pH}$ gives $E_0 = \Phi_0^2/2L_n \simeq 1.4 \times 10^{-8} \text{ J}$, while, with $T_c = 9.1 \text{ K}$, the thermal energy is $k_B T_c/2 = 6 \times 10^{-23} \text{ J}$.
- [17] R.J. Rivers, *J. Low Temp. Phys.* **124**, 41 (2001).